



PHENOLIC RESIN

APPLICATION:

Flexo / gravure inks, Deep Freeze, Spirit varnishes, Aniline inks, Rust preventive lacquers, Road marking paints. Petrol resistant paints, Printing Inks, Adhesives based on neoprene rubber solution.

ADVANTAGE:

Excellent hardness, Solvent resistance, Water resistance, Oil resistance

Technical Specification:

Property	Unit	Value
Appearance	---	Clear Lump
Color	CGS	4 Max
Melting point	o C	80 - 90
Acid value	---	Phenolic Acidity
Viscosity @ 30oC (Ford Cup B-4) 50% solution in Ethanol	Secs	25 - 30

The leaflet provides information based on experience and lab experiments, but values may vary in practical use. Customers should ensure product suitability and not base legal claims on the leaflet.



SHELF LIFE:

It is recommended that the material should be used within 12 months from the date of manufacture.

PACKING:

25 Kg paper bags.

Storage:

Store at dry and cool place between 18 to 23 °C in original sealed pack.

The leaflet provides information based on experience and lab experiments, but values may vary in practical use. Customers should ensure product suitability and not base legal claims on the leaflet.